

# BETEC<sup>®</sup> M-5

One-component waterproofing system by crystallisation for the protection of concrete against water penetration

---

## Product Description

BETEC<sup>®</sup>M-5 is a special blend of cement, quartz sand and active chemicals in powder form for the protection of concrete against water penetration. Betec M-5 provides in-depth waterproofing and protection against water penetration by pressure of osmosis and reacts with moisture and free lime in the concrete, forming crystals which seal the capillaries and pores for waterproofing/damp-proofing of new and existing structures.

Betec M-5 can be applied by one of the following methods:

1. Slurry application by brush or spray for in-depth crystallisation of concrete post treatment.
2. Dry powder sprinkling onto lean concrete before laying the slab or on freshly placed concrete surface.
3. Integrated as a concrete additive at the time of batching, allowing catalytic crystalline growth within the concrete making it waterproof.

## Product Advantages

- Offers long-term waterproofing even under high water pressure, both on the positive and negative side.
- Fully integrated with the concrete, becoming an integral part of the concrete structure.
- Waterproofs concrete deeply due to the penetration of insoluble crystals in the capillary system. Crystallisation starts from the surface and continues to penetrate into the concrete over time.
- Reduces shrinkage and hairline cracks.
- Seals hairline cracks that may occur from subsequent shrinkage or settlement, and static cracks.
- Can be applied on wet surface when used as a slurry coating.
- Non-toxic and odour free.

## Applications

- Floor, basement wall and slab
- Bathroom, balcony, wet area and planter box
- Water-retaining structure
- Parking deck

## Physical Properties

Apply the first coat of Betec M-5 mixed materials onto the prepared surface using a brush, trowel, squeegee or roller in a stifling action.

PROPERTIES	UNIT	TYPICAL VALUE
------------	------	---------------

Initial Set	min	≥ 20
Final Set	hr	≤ 24
Water Pressure Resistance	Mpa	≥ 0.8*
Water Penetration @ 5 bars for 72 hrs	mm	12

Typical test values may represent average values from samples tested. Test methods noted may be modified.

\* Typical test values based on slurry application with 2 coats at 1.5 to 2mm thickness.

## Supply

PACK SIZE	PACKAGING	SHELF LIFE
20kg	Plastic pail	18 months storage under dry conditions

## Cleaning

All tools and equipment should be cleaned immediately with clean water after use. Hardened material can only be removed mechanically.

## Consumption

- For slurry application: Apply Betec M-5 at 0.8 to 1.2kg / coat / m<sup>2</sup> in 2 coats by brush or spray.
- For dry sprinkle application: Apply Betec M-5 at 1.2kg / m<sup>2</sup> onto lean concrete binding prior to placing fresh concrete.
- For integration with concrete: Add Betec M-5 at the rate of 0.8% to 1.2% of the cementitious content on a pre-approved mix design.

## Health and Safety

Read the product label and Material Safety Data Sheet (MSDS) before use. Users should acquaint themselves with all risk and safety phrases. MSDS can be obtained from GCP Applied Technologies.

## Technical Services

For assistance with working drawings for projects and additional technical advice, please contact GCP Applied Technologies Technical Services.



032-031-1669

## Installation by Slurry Application

### Surface Preparation

- Chase out all holes and voids and fill with appropriate type of Mortar from GCP Applied Technologies to provide a smooth, level surface. Mortar joints should be flush pointed.
- Remove all bitumen, oil, grease, dirt and other surface contaminants by wire brushing and pressure washing.
- Cut back any protrusions.
- Pre-water or damp the surface prior to application

### Mixing

- Mix Betec M-5 with water at water-cement ratio of 1:2.5
- Mix until a homogeneous slurry, free from all lumps is formed.
- Scrape any unmixed material from the side of the mixing container with a trowel and mix in.
- Mixed materials should be used within 20 minutes, recommended not more than 30 minutes. It can be slurred again when hard but DO NOT ADD WATER AGAIN.

### Application

- Apply the first coat of Betec M-5 mixed materials onto the prepared surface using a brush, trowel, squeegee or roller in a stifling action.
- Apply the second coat finish depending on site conditions and film thickness required.
- Before applying the second coat in alternate direction, leave the first coat to dry approximately 1- 2 hours depending on the thickness, recommended not more than 24 hours.
- If overcoating is done more than 24 hours after applying the previous coat, or the previous coat has already dried out, the surface must be pre-wetted again.
- Protect treated surfaces from rainfall, frost and puddling of water and requirements.

### Installation by dry sprinkle application:

- The surface does not need to be dry, but standing water must be removed.
- Remove all debris and laitance.
- Pre-calculate the amount of Betec M-5 required and dry sprinkle them evenly throughout the area prior to concrete placement.

### Cure and Protection

- Sprinkler curing is needed when the coat is in semi-dry condition. Curing water must be clean and water flow should be managed to prevent from damage of the coating.
- In open conditions with temperature from 10°C - 20°C, sprinkler curing is needed every 3 - 5 hours.
- Curing needed when the coat turns white.
- Protect treated surfaces from rainfall, frost and puddling of water and requirements.

### Installation by integration with concrete application:

- Mix Betec M-5 with a small amount of water to form slurry.
- Add required amount into the central batching mixer or ready-mix concrete truck. Ensure an even and homogeneous mix is achieved throughout before discharging the concrete.
- For advice on concrete mix design, please contact GCP Applied Technologies Technical Service.

[gcpat.my](http://gcpat.my) | For technical information: [asia.enq@gcpat.com](mailto:asia.enq@gcpat.com)

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898 India +91 124 402 8972 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133 Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Betec is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2017 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 2325 Lakeview Parkway, Alpharetta, GA 30009, USA

GCP Applied Technologies (Malaysia) Sdn. Bhd, 7 Lorong CJ 1/1A, Off Jalan Balakong, 43200 Cheras Jaya, Kuala Lumpur, Malaysia

This document is only current as of the last updated date stated below and is valid only for use in Malaysia. It is important that you always refer to the currently available information at the URL below to provide the most current product information at the time of use. Additional literature such as Contractor Manuals, Technical Bulletins, Detail Drawings and detailing recommendations and other relevant documents are also available on [www.gcpat.my](http://www.gcpat.my). Information found on other websites must not be relied upon, as they may not be up-to-date or applicable to the conditions in your location and we do not accept any responsibility for their content. If there are any conflicts or if you need more information, please contact GCP Customer Service.

Last Updated: 2022-11-24

[gcpat.my/solutions/products/betec-grouts-and-cementitious-mortars/betec-m-5](http://gcpat.my/solutions/products/betec-grouts-and-cementitious-mortars/betec-m-5)